

EPS[®] 2535

Suggested Formulation

EPS[®] 2535 offers exceptional corrosion resistance without the use of anticorrosive pigments and additives. This resin provide paint formulators with a waterborne alternative to alkyd resins, which can be used for maintenance coatings and general product finishes on ferrous and non-ferrous metal, wood, and plastic substrates.

PROPERTIES

- Excellent gloss development and retention
- Excellent adhesion to ferrous and non-ferrous metal substrates
- Excellent early water resistance and broad solvent compatibility
- Allow formulators to use typical hydrophilic solvents (EB, DB), and hydrophobic solvents (DPnB, Texanol) for superior performance

COMMON APPLICATIONS

Primer, Topcoat

Specifications

Weight Solids	45.0 ± 0.7%
Weight/Gallon	8.70 ± 0.10
pH	7.5 – 8.5

Typical Properties

Volume Solids	42.0 ± 0.7%
MFFT	56° C
Volatile(s)	Water

FORMULATING GUIDELINES

The following guidelines are offered to assist the paint formulator in achieving the high-performance properties offered by EPS 2535. Several suggested paint formulations are also available for reference.

Pigment Volume Concentration (PVC)

Formulating at the correct PVC is critical in optimizing corrosion resistance of coatings. For best results in high gloss coatings, the PVC should be formulated as low as possible (less than 20 % is suggested) to obtain maximum corrosion protection and gloss development. In primer formulations, where a higher PVC or the use of corrosion inhibitive pigments is desired, it is necessary to use a higher level of dispersant. Formulas at a PVC of approximately 40% still show good long-term viscosity stability, as well as resistance to settling and separation. The use of AMP-95

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com

4/9/2021

TECHNICAL SUPPORT: These guidelines are offered to assist the paint formulator in achieving the high performance properties noted and are offered for illustration purposes only; the paint formulator bears sole responsibility for the performance of the final coating product.

SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscsa.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscsa.com/galleries/pdfs/salesterms.pdf>.

(Angus), at a level of 1 pound per 100 gallons, has also been found effective in terms of long term stability, as well as aiding in pigment dispersion and grind base stability of these higher PVC coatings.

Dispersants

Tamol 681(Dow), Byk 190 (BYK), and Disperse-Ayd W-22 (Elementis) are recommended for use with EPS 2535. Each should be evaluated and compared to see which fits your particular formulating needs. Disperse-Ayd W22 has been found most effective in high PVC (40%) primer formulas (such as EPS 2535 SP-3). This formula shows a slightly higher level of dispersant than would be used at lower PVCs, although this level was determined necessary for the proper balance of required properties.

Co-solvents

The use of DPnB (25% on resin solids) is recommended to form films as low as 40°F while offering excellent corrosion resistance and excellent open dry times for finishing large objects. Small additions of plasticizer, such as Paraplex WP-1, Santicizer 160, or KP140 may enhance the film properties. Other co-solvents, such as Texanol (25% on solids), PnB (30%) have been found to be adequate when used with EPS 2535, albeit with slightly less performance.

Thickeners

Most rheological additives work well with the EPS 2535. It may be necessary at times to use a package of Rheology modifiers, in order to attain viscosity control as well as proper sag resistance. Among those showing particular success were Acrysol RM-825 and Acrysol RM-2020 (Dow), Tafigel PUR-60 (Munzing), Rheolate 1 (Elementis), and Attagel 50 (BASF).

Corrosion Inhibitive Pigments

While EPS 2535 has been found stable with a large variety of corrosion inhibitors, the proper balance of corrosion resistance in regard to properties such as viscosity stability, settling and desired gloss can be difficult to attain. In high PVC primer formulas, EPS has determined that a unique synergy makes the combination of SZP-391 (Halox) and Shieldex AC-5 (Grace), at levels of 25 and 15 pounds per 100 gallons, respectively, an ideal choice to attain all properties.

Flash Rust Inhibitors

The addition of a flash rust additive to DTM paints is recommended. Sodium nitrite is recommended at a maximum level of one pound per 100 gallons of paint.

Defoamers

For difficult foaming issues, or during formulation of higher PVC coatings, it may be necessary to use a combination of defoaming products. Strong defoamers, such as BYK 024 (BYK), or FoamStar SI 2210 (BASF), may not be as effective for microfoaming. In this case, an additional anti-foam agent may be required. Laboratory results have found Foamaster 111, Foamaster S (BASF) and Surfynol DF-210 (Evonik) to be adequate for this purpose. Most anti-foam agents evaluated with EPS 2535 proved effective to various degrees.

pH

The pH of paints produced with EPS 2535 should be 8.0-9.5. AMP-95 (Angus) and ammonium hydroxide are recommended for pH adjustments.

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com

4/9/2021

TECHNICAL SUPPORT: These guidelines are offered to assist the paint formulator in achieving the high performance properties noted and are offered for illustration purposes only; the paint formulator bears sole responsibility for the performance of the final coating product.

SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscsa.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscsa.com/galleries/pdfs/salesterms.pdf>.

Suggested Formulation

EPS 2535 WHT SG2 - White DTM Corrosion Resistant Semi-Gloss

<u>Pounds</u>	<u>Gallons</u>	<u>Raw Material</u>	<u>Supplier</u>	<u>Instructions</u>
50.00	6.00	Water		Add with good agitation
20.00	2.27	Disperbyk 190	BYK	
2.00	0.28	Surfynol 104A	Evonik	
1.00	0.12	BYK 024	BYK	
2.00	0.25	Amp-95	Angus	
100.00	2.87	TiONA 596	Cristal	
40.00	2.67	Shieldex AC-5	Grace	
25.00	1.05	Sericron 5M	Specialty Minerals	Disperse to 6NS
542.00	62.30	EPS 2535	EPS	Premix emulsion with water.
50.00	6.00	Water		Add grind paste.
33.30	4.00	Water		Premix the next four items
10.00	1.20	4% Sodium Nitrite Soln.		
1.50	0.16	Nuosept 95	Troy	
79.30	10.37	DPnB		Add with good agitation.
2.00	0.23	RM-825	Dow	Premix with water, adjust viscosity.
<u>2.00</u>	<u>0.24</u>	Water		
960.10	100.00	Totals		

Formulation Parameters

Weight Solids	44.00	%
Volume Solids	34.20	%
Weight / Gallon	9.60	lb/gal
Pigment Volume Conc.	20.11	%
Pigment/Binder"	0.68	
VOC	218	g/l

Typical Paint Properties

Viscosity (Stormer)	70 – 80 KU
pH	8.5 - 9.5
Color	White
Gloss (60°)	< 30

Suggested Application Methods

Spray

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com

4/9/2021

TECHNICAL SUPPORT: These guidelines are offered to assist the paint formulator in achieving the high performance properties noted and are offered for illustration purposes only; the paint formulator bears sole responsibility for the performance of the final coating product.

SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscsa.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscsa.com/galleries/pdfs/salesterms.pdf>.