

EPS[®] 2533 Suggested Formulation

EPS[®] 2533 is a styrenated acrylic emulsion offering exceptional ink and tannin blocking characteristics, as well as excellent adhesion and early water resistance. EPS[®] 2533 provides paint formulators a waterborne alternative to solvent-based primers and is ideal for use as a universal primer or low gloss topcoat on ferrous and non-ferrous metal, cementitious, wood and plastic substrates.

PROPERTIES

- Exceptional alkali resistance, ideal for use on "hot" cementicious substrates
- Exceptional tannin stain block
- Exceptional water-based and solvent-based ink marker stain block
- Exceptional exterior durability
- Excellent corrosion resistance even without the use of anticorrosive pigments or additives
- Excellent early water resistance
- Excellent adhesion to ferrous and non-ferrous metal substrates, glossy alkyds and chalky substrates
- Made without APEO surfactants

Specifications

| Weight Solids | 45.5 +/- 0.7% |
|---------------|---------------|
| Weight/Gallon | 8.60 +/- 0.10 |
| pH | 7.0 - 8.0 |

Typical Properties

| Volume Solids | 43.7 +/- 0.7% |
|---------------|---------------|
| MFFT | 9° C |
| Volatile(s) | Water |

Suggested Coalescing Solvent(s) (% Solvent on Binder Solids – Pass 40°F LTC Test)

Texanol / EPS 9147 or Blends 5 - 6%

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com

2/5/2021

TECHNICAL SUPPORT: These guidelines are offered to assist the paint formulator in achieving the high performance properties noted and are offered for illustration purposes only; the paint formulator bears sole responsibility for the performance of the final coating product.

SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscca.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at https://www.epscca.com/galleries/pdfs/salesterms.pdf.



Suggested Formulation

Formula: EPS 2533 WHT1 (186-1, 3/3/09) Universal Stain-Blocking Primer – White

| Pounds | Gallons | Raw Material | <u>Supplier</u> | Instructions |
|-----------------------------|------------------------------|--------------------------------------------------------------------------|-----------------|-------------------------|
| 66.6 | 8.00 | Water | | Add with good agitation |
| 15.0 | 1.69 | Tamol 2001 | Dow | |
| 2.0 | 0.28 | Surfynol 104A | Evonik | |
| 1.0 | 0.13 | Drewplus L-475 | Troy | |
| 4.0 | 0.51 | AMP 95 | Angus | |
| 150.0 | 4.38 | Ti-Pure R902 | Chemours | |
| 100.0 | 4.43 | Cal White | Imerys | |
| 15.0 | 0.32 | Zoco 103 | Zochem | Grind to 6 NS |
| 619.2 | 72.00 | EPS 2533 | EPS | Letdown |
| | | | | |
| 2.0 | 0.26 | Drewplus L-475 | Troy | Add with good agitation |
| 2.0 1.5 | 0.26 0.16 | Drewplus L-475 Nuosept 498 | Troy Troy | Add with good agitation |
| | | | | Add with good agitation |
| 1.5 | 0.16 | Nuosept 498 | Troy | Add with good agitation |
| 1.5 14.1 | 0.16 1.61 | Nuosept 498 EPS 9147 | Troy | Add with good agitation |
| 1.5 14.1 35.0 | 0.16 1.61 3.75 | Nuosept 498 EPS 9147 Ethylene Glycol | Troy | Add with good agitation |
| 1.5 14.1 35.0 10.0 | 0.16 1.61 3.75 1.20 | Nuosept 498 EPS 9147 Ethylene Glycol Sodium Nitrite (4%) | Troy | Add with good agitation |

Formulation Parameters

| Weight Solids | 54.7 | % |
|----------------------|----------|---------|
| Volume Solids | 43.5 | % |
| Weight / Gallon | | # / gal |
| Pigment Volume Conc: | 22.49 | % |
| Pigment / Binder | 0.94 : 1 | |
| VOC | 100 | g / L |
| | 0.83 | # / gal |

Typical Paint Properties

| Viscosity (Stormer) | 90 – 100 KU |
|---------------------|-------------|
| рН | 9.0- 10.0 |
| Color | White |

Suggested Application Methods Brush, Roller, Airless Spray

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com

2/5/2021

TECHNICAL SUPPORT: These guidelines are offered to assist the paint formulator in achieving the high performance properties noted and are offered for illustration purposes only; the paint formulator bears sole responsibility for the performance of the final coating product.

SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscca.com.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at https://www.epscca.com/galleries/pdfs/salesterms.pdf.