

# **EPS<sup>®</sup> 2156D**

All-Acrylic Emulsion

## MARKET SEGMENT: ADHESIVES

#### COMMON APPLICATIONS: PRESSURE-SENSITIVE ADHESIVES

EPS<sup>®</sup> 2156D is an all-acrylic emulsion for pressure-sensitive adhesive applications. Typical values below are for the neat polymer.

#### **PERFORMANCE BENEFITS**

- Low foaming
- 180° Peel (PSTC-101) 11 oz/in
- Polyken Probe Tack (ASTM D2979) 230 g/cm<sup>2</sup>
- Static Shear (PSTC-107) >10,000 minutes (1"x1"x1 kg)

### TYPICAL PROPERTIES

Weight Solids	55.5 ± 1.0%
Weight/Gallon	8.59 ± 0.10
рН	7.0 - 9.0
Volume Solids	54.2 +/- 1.0
Тց	-41° C

These typical properties do not represent specifications.

Questions? Call EPS Customer Service @ 1-800-654-4242 / Email: info@eps-materials.com SDS: For details on health, safety and handling information, Safety Data Sheets (SDS) are available at www.epscca.com. 4/23/2024

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at https://www.epscca.com/galleries/pdfs/salesterms.pdf.